

## 試驗報告

報告編號: KB-11-04198ZA

C-11-10289

頁數: 1 OF 2

報告日期: 100 年 05 月 05 日

工主承委供樣結  
程辦包  
名機  
稱關商位商稱位  
稱: 臺灣桃園國際機場外捷運系統設計案 (C303A) 施工工程  
關: 中鼎/萬鼎工程股份有限公司 10003 製造工程處  
商: 新亞建設開發股份有限公司  
位: 新亞建設開發股份有限公司  
商: 聯新工程股份有限公司; 富盛玻璃工程行; 全光武玻璃科技股份有限公司  
稱: 強化清玻璃(19mm)  
位: 115.18 車路橋光學玻璃, 膠合熱硬化清玻璃(站務室, 漆板玻璃牆, 電梯玻璃, 金屬雨庇, 玻璃護欄, 標準柵欄 TYPE F 鋁窗)  
人員: 中鼎/萬鼎(張居正); 新亞建設(歐元志)  
人員: 中鼎/萬鼎(張居正); 新亞建設(歐元志)  
日期: 100 年 04 月 11 日  
日期: 100 年 04 月 15 日  
日期: 100 年 04 月 15 日~100 年 05 月 05 日  
方法: CNS 2218(1985) 強化玻璃檢驗法  
註: 1. 以上資料由顧客提供(收件及試驗日期除外)  
2. 本樣品由 SGS 材料及工程實驗室-台中(請書號碼: TB-11-01331W C-11-06996, 收件日期: 100 年 04 月 12 日)轉送至本實驗室執行本報告所示之試驗項目。

本與正本相符

## 試驗結果:

一、

測試項目	樣品編號	測試結果	CNS 2217(1985)規範要求
耐衝擊性	1 號	無破壞	6 塊樣品中如破壞 1 塊以下時判定為合格, 3 塊以上時判定為不合格; 如破壞 2 塊時, 另取 6 塊樣品再行測試, 其 6 塊樣品均不破壞時即為合格。
	2 號	無破壞	
	3 號	無破壞	
	4 號	無破壞	
	5 號	無破壞	
	6 號	無破壞	
破碎試驗(塊)	7 號	41.0	破片數量須在 40 塊以上
	8 號	42.5	
	9 號	40.5	
	10 號	41.0	
	11 號	40.5	

-----1-----

蔡聖仁

報告簽署人

本報告若有提供規範值時, 該規範值僅供參考, 合格之判定以委託單位實際要求為準

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明, 此報告結果僅對測試之樣品負責。本報告未經本公司書面許可, 不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.