

試驗報告



報告編號：KB-25-09343

C-25-27153

頁數：1 OF 2

報告發行日期：114年10月21日

委託單位：全光武玻璃科技有限公司
 樣品名稱：5mm+5mm 膠合玻璃透明膜
 送驗人員：全光武玻璃科技有限公司(黃閔暘)
 收件日期：114年09月23日
 試驗日期：114年09月23日~114年10月21日
 試驗方法：CNS 1183:2011
 備註：1.以上資料(會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
 2.除非另有說明，此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	樣品編號	試驗結果
耐衝擊性	1 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：1900 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。
	2 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：1900 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。
	3 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：1200 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。
	4 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：2400 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。
	5 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：3000 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。
	6 號	落球直徑：63.5 mm；落球重量：1042g；落距高度：2400 mm，玻璃破裂。
		玻璃破裂後無造成中間膜斷裂或曝露出部份之情形。

----- 1 -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準


報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：KB-25-09343

C-25-27153

頁數：2 OF 2

報告發行日期：114年10月21日

試驗結果：

二、

試驗項目	樣品編號	試驗結果
翹曲性(%)	1 號	弓形翹曲 0.03

三、

試驗項目	樣品編號	試驗結果
厚度量測(mm)	1 號	10.1
外觀檢測	1 號	中間膜無產生氣泡
		中間膜無雜質
		中間膜無裂痕
		無殘缺
		無波紋
		無模糊陰影及傷痕
		中間膜之膜皺紋及筋紋

註：

- 1.樣品描述：膠合玻璃。
- 2.本報告耐衝擊性、翹曲性試驗為 TAF 認可項目，其餘則非。
- 3.本試驗報告衝擊試驗之試驗地點為高雄市仁武區後安里永宏巷 40-6 號，其它試驗之地點同實驗室地址。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.